

# **HEAT-RESISTING STEELS**

# **Application Segments**

Oil & Gas/CPI

#### **Available Product Variants**

Long Products

### **Product Description**

BÖHLER H500RB (Alloy 800, 800HT) is an austenitic, high-temperature iron-nickel-chromium alloy with good creep rupture strength at temperatures above 600°C. This material also has good resistance in oxidising, carburising and sticking atmospheres with good workability.

With a nickel content of more than 30%, this material has little tendency to precipitate sigma phase. In addition to the good mechanical long-term properties, BÖHLER H500RB is resistant to oxidation and carburisation up to approx. 1000°C. In certain temperature ranges, it shows resistance to sulphurous media.

The original Alloy 800 is increasingly being replaced in the market by the variants 800H and HT. These can be solution annealed and therefore have improved creep rupture properties at high temperatures.

The material BÖHLER H500RB fulfils the properties of Alloy 800 as well as Alloy 800H and 800HT by controlled contents of carbon,

The material BOHLER H500RB fulfils the properties of Alloy 800 as well as Alloy 800H and 800HT by controlled contents of carbon, aluminium, titanium, silicon and manganese as well as controlled sum content of Al + Ti. In the case of Alloy 800H and HT, special solution annealing significantly increases the creep rupture strength at temperatures above 600°C.

## **Process Melting**

Airmelted

# **Applications**

- > Chemical industry general
- > Oil & Gas / CPI
- > Oil & Gas, CPI & Renewables
- > Heat Exchanger
- > Burner Nozzles
- > Other Oil and Gas + CPI components
- > High temperature components
- > Fasteners, Bolts, Nuts
- > Tubular Products, Flanges, Fittings

#### Technical data

Material designation					
Alloy 800					
Alloy 800H	Market grade				
Alloy 800HT					
1.4876	SEL				
1.4959	SEL				
X10NiCrAlTi32-21	- FNI				
X8NiCrAlTi32-21	EN				
N08800					
N08810	UNS				
N08811					

Standards		
	10302	EN ISO
	B408	ASTM





# Chemical composition (wt. %)

С		Si	Mn	Р	S	Cr	Ni	Cu	Ti	Al	Fe
0.	06 to 0.10	max. 1.0	max. 1.5	max. 0.045	max. 0.015	19.0 to 23.0	30.0 to 35.0	max. 0.75	0.25 to 0.60	0.25 to 0.60	min. 39.5

Refers to ASTM B408 - Alloy N08800 N08810 N08811 | AI + Ti 0.85 - 1.20

#### **Delivery condition**

Solution Annealed + Quenched			
Tensile Strength (MPa)	min. 515		
Yield Strength (MPa)	min. 205		

#### Round Bars and Wire Rod (if any)

Diameter					
mm					
ROLLED					
12.50	-	130.00			
FORGED					
130.10	-	203.20			

More information regarding MOQ, lengths and tolerances upon request. Flat bars on request.

If other available product variants are listed in addition to long products, please note that these may differ in terms of melting process, technical data, delivery and surface condition as well as available product dimensions. For mandatory technical specifications, other requirements and dimensions, please contact our regional voestalpine BÖHLER sales companies. The data contained in this brochure is merely for general information and therefore shall not be binding on the company. We may be bound only through a contract explicitly stipulating such data as binding. Measurement data are laboratory values and can deviate from practical analyses. The manufacture of our products does not involve the use of substances detrimental to health or to the ozone layer.

#### voestalpine BÖHLER Edelstahl GmbH & Co KG

Mariazeller Straße 25 8605 Kapfenberg, AT T. +43/50304/20-0 E. info@bohler-edelstahl.at https://www.voestalpine.com/bohler-edelstahl/de/

