

NI-BASE ALLOYS

Application Segments

Aerost	oace

Available Product Variants

Long	Products*

Semi-Finished Products / Billet

Product Description

BÖHLER L718HCB is a corrosion and heat resistant nickel alloy - precipitation hardenable - in the form of bars, forging and forging stock. High resistance to creep and stress-rupture up to $1300^{\circ}F$ ($704^{\circ}C$) and oxidation resistance up to $1800^{\circ}F$ ($982^{\circ}C$). High duty parts and components for gas turbines, aerospace engines, high-speed airframe parts such as disks, buckets, spacers and high temperature bolts and fasteners.

Compared to standard alloy 718 AMS limits, Cb in L718HCb is adjusted in the upper range of the standard limits in order to enhance mechanical properties. L718HCb is typically used for high temperature bolting and fasteners.

Process Melting

VIM + VAR

Applications

> Other Aerospace Components

- > Turbine and Engine Parts (Aerospace)
- > Aerospace

Technical data

Material designation		
Alloy 718	Market grade	
2.4668	SEL	
NiCr19NbMo/ NiCr19Fe19Nb5Mo3	EN	
NC19FCNb		
N07718	UNS	

Standards		
	5662	
	5962	AMS
	5663	



^{*} Presented data refer exclusively to long products. Please observe the detailed explanations at the end of the data sheet (pdf).



Chemical composition (wt. %)

С	Si	Mn	P	S	Cr	Мо	Ni	Cu	Со	Ti	Al	Nb	В	Fe	Pb	Bi	Se
max. 0.08	max. 0.35	max. 0.35	max. 0.015	max. 0.015	17.00 to 21.00	2.80 to 3.30	50.00 to 55.00	max. 0.30	max. 1.00	0.65 to 1.15	0.20 to 0.80	4.75 to 5.5	max. 0.006	REM	max. 5ppm	max. 0.3ppm	max. 3ppm

Related to AMS5662

Delivery condition

Solution annealed	
Hardness (HB)	max. 277 bars and forging stock, max 254 mm diameter

Round Bars and Wire Rod (if any)

	Diameter MOQ ex			Length m			Tolerance				
	ROLLED										
5.01	-	11.00	250	3.00	-	4.00	IT h/k 9				
12.20	-	40.00	550	3.00	-	4.00	+/-0,1mm				

If other available product variants are listed in addition to long products, please note that these may differ in terms of melting process, technical data, delivery and surface condition as well as available product dimensions. For mandatory technical specifications, other requirements and dimensions, please contact our regional voestalpine BÖHLER sales companies. The data contained in this brochure is merely for general information and therefore shall not be binding on the company. We may be bound only through a contract explicitly stipulating such data as binding. Measurement data are laboratory values and can deviate from practical analyses. The manufacture of our products does not involve the use of substances detrimental to health or to the ozone layer.

voestalpine BÖHLER Edelstahl GmbH & Co KG

Mariazeller Straße 25 8605 Kapfenberg, AT T. +43/50304/20-0 E. info@bohler-edelstahl.at https://www.voestalpine.com/bohler-edelstahl/de/

