

CORROSION RESISTANT STEELS - MARTENSITIC PRECIPITATION HARDENING (PH) STEELS

			_		
Λ 👝	m li n	ation	Sec		nto
Δ II	L 1111 (.)	411C)[ши	HIS
, ,	$\mathbf{p}_{11}\mathbf{p}_{1}$	auoi		41110	1110

Aerospace Land Based Turbines

Available Product Variants

Long Products* Semi-Finished Products / Billet Plates

Product Description

BÖHLER N700 SA is a premium aerospace-quality corrosion-resistant steel available in bars, wire, and forgings with diameters/thicknesses up to 203 mm in the solution-annealed condition, as well as starting material of any size for forging purposes. It is a martensitic, precipitation-hardenable chromium-nickel-copper steel with high strength and toughness. Further strength increases can be achieved through cold working and subsequent precipitation hardening.

These products are typically used for parts requiring corrosion resistance and high strength up to 316 °C, but their use is not limited to such applications.

Certain processing methods and operating conditions can make these products susceptible to stress corrosion cracking.

For applications such as bolted joints where stress corrosion is possible, the product should be aged for at least 4 hours at the highest temperature compatible with the strength requirements, but in no case lower than $552\,^{\circ}\text{C}$.

Process Melting

Airmelted

Applications

> Aerospace

> Other Aerospace Components

Standarde

> Structural parts (Aerospace)

Technical data

Material designation				
17-4 PH	Market grade			
1.4548	SEL			
X5CrNiCu17-4 EZ6CNU17.04	EN			
S17400	UNS			
630	AISI			

Stariuarus		
	10088-3	EN ISO
	A564	ASTM
	5643	AMS



^{*} Presented data refer exclusively to long products. Please observe the detailed explanations at the end of the data sheet (pdf).



CORROSION RESISTANT STEELS - MARTENSITIC PRECIPITATION HARDENING (PH) STEELS

BÖHLER N700SA

Chemical composition (wt. %)

С	Si	Mn	Р	S	Cr	Мо	Ni	Cu	Nb
max. 0.07	max. 1.00	max. 1.00	max. 0.040	max. 0.030	15.00 to 17.50	max. 0.50	3.00 to 5.00	3.00 to 5.00	5xC to 0.45

Related to AMS 5643

Delivery condition

Solution annealed						
Hardness (HB)	max. 363 bars, hot or cold finished, forgings					
Tensile Strength (MPa)	max. 1,207 for wire products					

Round Bars and Wire Rod (if any)

Diameter		eter	MOQ ex mill	Length		jth	Tolerance			
	mm kg m									
	ROLLED									
5.50	-	12.49	1,100	3.00 - 4.00		4.00	IT h/k 11			
12.50	-	55.00	1,200	3.00 -		4.00	IT h/k 11			
55.01	T-	120.00	2,297	3.00 -		4.00	IT h/k 11			
120.01	-	140.00	2,300	3.00 - 5.00		5.00	IT h/k 14			
	FORGED									
140.01	-	180.00	1,320	2.00 -		5.00	IT h/k 14			
180.01	-	210.00	1,496	2.00 -		5.00	IT h/k 14			

Flat Bars

Width mm		Thickness mm		MOQ ex mill kg	Length m			Tolerance		
	ROLLED									
15.00	-	121.00	8.00	-	86.00	1,100	3.00	-	4.00	LN 1017
120.00	-	150.00	25.00	-	85.00	1,100	3.00	-	4.00	LN 1017
150.00	-	275.00	20.00	-	100.00	1,100	3.00	-	4.00	LN 1017
275.00	-	330.00	25.00	-	80.00	1,100	3.00	-	4.00	LN 1017

If other available product variants are listed in addition to long products, please note that these may differ in terms of melting process, technical data, delivery and surface condition as well as available product dimensions. For mandatory technical specifications, other requirements and dimensions, please contact our regional voestalpine BÖHLER sales companies. The data contained in this brochure is merely for general information and therefore shall not be binding on the company. We may be bound only through a contract explicitly stipulating such data as binding. Measurement data are laboratory values and can deviate from practical analyses. The manufacture of our products does not involve the use of substances detrimental to health or to the ozone layer.

voestalpine BÖHLER Edelstahl GmbH & Co KG

Mariazeller Straße 25 8605 Kapfenberg, AT

T. +43/50304/20-0

E. info@bohler-edelstahl.at

https://www.voestalpine.com/bohler-edelstahl/de/

