

CORROSION RESISTANT STEELS -MARTENSITIC PRECIPITATION HARDENING (PH) STEELS

Application Segments

Aerospace

Available Product Variants

Long Products*	Semi-Finished Products / Billet	Plates

* Presented data refer exclusively to long products. Please observe the detailed explanations at the end of the data sheet (pdf).

Product Description

This specification covers a premium aircraft-quality corrosion-resistant steel in the form of bars, wire, forgings up to 12.0 inches (305 mm) in diameter or least distance between parallel sides in the solution heat treated condition and stock of any size for forging.

It is a martensitic precipitation hardenable chromium-nickel-copper steel possessing high strength and toughness. Further strength increments can be obtained by cold forming, followed by a precipitation hardening treatment.

These products have been used typically for parts requiring corrosion resistance and high strength up to 600 °F (316 °C) with good ductility and strength in the transverse direction in large section sizes but, but usage is not limited to such applications.

Certain processing procedures and service conditions may cause these products to become subject to stress-corrosion cracking.

Process Melting

Airmelted + VAR

Applications

> Aerospace

> Other Aerospace Components

Engineering

> Structural parts (Aerospace)

Technical data

Material designation		St	andards		
15-5 PH	Market grade		,	4564	ASTM
1.4545	SEL			5659	AMS
X5CrNiCu15-5	EN				



S15500 UNS



CORROSION RESISTANT STEELS -MARTENSITIC PRECIPITATION HARDENING (PH) STEELS



Chemical composition (wt. %)

C Si Mn P S Cr Mo Ni Cu Nb max. 0.07 max. 1.00 max. 0.030 max. 0.015 14.00 to 15.50 max. 0.50 3.50 to 5.50 2.50 to 4.50 5xC to 0.50										
max. 0.07 max. 1.00 max. 1.00 max. 0.030 max. 0.015 14.00 to 15.50 max. 0.50 3.50 to 5.50 2.50 to 4.50 5xC to 0.0	С	Si	Mn	Р	S	Cr	Мо	Ni	Cu	Nb
	max. 0.07	max. 1.00	max. 1.00	max. 0.030	max. 0.015	14.00 to 15.50	max. 0.50	3.50 to 5.50	2.50 to 4.50	5xC to 0.45

Related to AMS 5659 type 1

Delivery condition

Solution annealed	
Hardness (HB)	max. 363 bars, hot or cold finished, forgings
Tensile Strength (MPa)	max. 1,207 for wire products

Round Bars and Wire Rod (if any)

Diameter			MOQ ex mill	1	.eng	jth	Tolerance			
mm			kg	m						
ROLLED										
5.01	-	12.49	1,100	3.00	-	4.00	IT h/k 11			
12.50	-	55.00	1,200	3.00	-	4.00	IT h/k 11			
55.01	-	120.00	2,300	3.00	-	4.00	IT h/k 11			
120.01	-	140.00	2,300	3.00	-	5.00	IT h/k 14			
FORGED										
140.01	-	203.20	2,350	2.00	-	5.00	IT h/k 14			
203.21	-	304.80	3,500	2.00	-	5.00	IT h/k 14			

Flat Bars

N	Width Thickness		MOQ ex mill	Length			Tolerance			
	mm mm		kg	m						
	ROLLED									
15.00	-	121.00	8.00	-	86.00	1,300	3.00	-	4.00	LN 1017
120.00	-	150.00	25.00	-	85.00	2,550	3.00	-	4.00	LN 1017
150.00	-	275.00	20.00	-	100.00	2,550	3.00	-	4.00	LN 1017
275.00	-	330.00	25.00	-	80.00	2,550	3.00	-	4.00	LN 1017

If other available product variants are listed in addition to long products, please note that these may differ in terms of melting process, technical data, delivery and surface condition as well as available product dimensions. For mandatory technical specifications, other requirements and dimensions, please contact our regional voestalpine BÖHLER sales companies. The data contained in this brochure is merely for general information and therefore shall not be binding on the company. We may be bound only through a contract explicitly stipulating such data as binding. Measurement data are laboratory values and can deviate from practical analyses. The manufacture of our products does not involve the use of substances detrimental to health or to the ozone layer.

voestalpine BÖHLER Edelstahl GmbH & Co KG Mariazeller Straße 25 8605 Kapfenberg, AT T. +43/50304/20-0 E. info@bohler-edelstahl.at https://www.voestalpine.com/bohler-edelstahl/de/

