

HIGH SPEED STEELS

Available Product Shapes

Plates

Product Description

BÖHLER S393 MICROCLEAN – "Standardized"

This variant alloy complies with the ASTM A600 AISI T15 material standard. With MICROCLEAN technology, this material shows excellent reliability in many chip-cutting and cold-work steel applications.

Properties

High Toughness & Ductility

High Wear Resistance

Very high Compressive strength

Very high Edge Stability

High Grindability

Very high Hot Hardness

Chemical composition

C	Cr	V	W	Co
1.55	4.40	4.90	12.40	5.00

Physical Properties at 20°C / 68°F

For more information see www.voestalpine.com/boehler-edelstahl

voestalpine BÖHLER Edelstahl GmbH & Co KG

Mariazeller Straße 25

8605 Kapfenberg, AT

T. +43/50304/20-0

E. info@boehler-edelstahl.at

www.voestalpine.com/boehler-edelstahl

voestalpine

ONE STEP AHEAD.