

ADDITIVE MANUFACTURING POWDER

W722 AMPO / FE-BASED ALLOYS

Available Product Shapes

15 - 45 µm

45 - 90 µm

Product Description

Precipitation hardening nickel martensitic (marging) steel, material number 1.20709, which offers a good combination of strength and toughness. Can be printed very easily without additional heating of the building platform or chamber. The achievable hardness of 55 HRC makes this material a universal solution for tool steel applications in which conformal cooling is required, such as die casting applications.

Properties

Particle size distribution 15 - 45 µm:

D10[µm]	18 - 24
D50[µm]	29 - 35
D90[µm]	42 - 50
Apparent density*	≥ 3.5 g/cm ³

Measurement of particle size distribution according to ISO 13322-2 (Dynamic image analysis methods);

* Measurement of apparent density is based on ASTM B964 resp. DIN EN ISO 3923-1 and relates to our typical measured values

Achievable mechanical properties of printed part after heat treatment:

Tensile strength (Rm)	2030 ± 70 MPa
Yield strength (RP _{0.2})	1950 ± 70 MPa
Elongation (%)	6 ± 2
Hardness	53 ± 2 HRC
Impact toughness (ISO V)	18 ± 2 J

Applications

- > 3D Printing - direct metal deposition
- > 3D Printing - selective laser melting
- > Automotive
- > Automotive Racing
- > Civil and mechanical engineering
- > Forging Applications
- > High Pressure Die-Casting
- > Injection Molding
- > Mechanical Engineering / Machine Building General
- > Other Components
- > Powder for additive manufacturing
- > Unknown Components Application

Material designation

1.2709	SEL
Marage 300	Market grade

Chemical composition

C	Si	Mn	P	S	Mo	Ni	Co	Ti
≤ 0,03	≤ 0,10	≤ 0,15	≤ 0,01	≤ 0,01	4.90	18.00	9.30	1.10

Heat treatment

Solution annealing

Temperature (°C / °F)	820 / 1508 - 1508 / 2746.4	Soaking time: 1h / air, gas
-----------------------	-------------------------------	-----------------------------

Precipitation hardening

Temperature (°C / °F)	490 / 914 - 914 / 1677.2	Holding time: 6h / air
-----------------------	-----------------------------	------------------------

For more information see www.voestalpine.com/boehler-edelstahl

voestalpine BÖHLER Edelstahl GmbH & Co KG

Mariazeller Straße 25

8605 Kapfenberg, AT

T. +43/50304/20-0

E. info@boehler-edelstahl.at

www.voestalpine.com/boehler-edelstahl

W722 AMPO EN - 09.2021

voestalpine

ONE STEP AHEAD.