

FERRITIC AND MARTENSITIC STEELS, INCL. PRECIPITATION HARDENING STEELS

Available Product Shapes

Plates

Product Description

Pressplates for the production of decorative and technical laminates (electronic industry)
Carrier Plates for the production of decorative and technical laminates

Properties

Ground grit 80 – grit 500, Precipitation hardened to 45 - 50 HRC

Material designation		
~1.4542	SEL	
AISI: 630	AISI	

Chemical composition

C	Cr	Ni	Cu	Nb
≤ 0,05	16.50	4.00	4.00	0.35

For more information see www.voestalpine.com/boehler-edelstahl

voestalpine BÖHLER Edelstahl GmbH & Co KG

Mariazeller Straße 25

8605 Kapfenberg, AT

T. +43/50304/20-0

E. info@boehler-edelstahl.at

www.voestalpine.com/boehler-edelstahl

voestalpine

ONE STEP AHEAD.