

ADDITIVE MANUFACTURING POWDER

L718 API AMPO / NI-BASED ALLOYS

Available Product Variants

15 - 45 µm	45 - 90 µm
------------	------------

Product Description

The BÖHLER L718 AMPO is a hardenable nickel-base super alloy. This high heat-resistant material shows good strength properties at elevated temperatures up to 750 °C, as well as excellent creep resistance up to 700 °C. In addition, it shows excellent corrosion resistance and good printability. Essentially, the same properties can be achieved with printed components made from this powder as with bar material.

Process Melting

VIGA

Applications

- > 3D Printing - direct metal deposition
- > Automotive Racing
- > CPI (inc. LNG, Urea)
- > Other Components
- > Powder for additive manufacturing
- > 3D Printing - selective laser melting
- > Civil and mechanical engineering
- > Oil & Gas
- > Other Oil and Gas + CPI comps.
- > Automotive
- > Comp. for Industrial Gas Compressors
- > Oth. Automotive components (Turbochargers, Piston Rings, Sensors, etc.)
- > Other Power Generation Components

Technical data

Material designation	
Alloy 718API	Market grade
N07718	UNS
NiCr19NbMo/ NiCr19Fe19Nb5Mo3	EN

Chemical composition (wt. %)

C	Cr	Mo	Ni	Ti	Al	Nb	B	Fe
0.02	18	3	Rest	0.95	0.5	5	0.003	18.5

Powder Properties

Particle Size Distribution 15-45µm*

Typical Values [µm]	D10	D50	D90
	18-24	29-35	42-50

* Measurement of particle size distribution is based on ISO 13322-2 (Dynamic image analysis methods);

Apparent density** | min. 3.5 g/cm³

** Flowability and apparent density are based on DIN EN ISO 4490 resp. DIN EN ISO 3923-1.

Mechanical Properties

With according Heat Treatment

Tensile strength (Rm)	1,290 187,099 to 1,390 201,602 MPa psi
Yield strength (RP _{0.2})	1,050 152289.5 to 1,110 160991.8 MPa psi
Elongation	26 to 32 %
Hardness	41 to 47 HRc
Impact Toughness (ISO-V)*	58 to 68 J

* a -60 °C

Mechanical strength according to heat treatment API6acra - 150ksi

For more information see <https://www.voestalpine.com/boehler-edelstahl/de/>

The data contained in this brochure is merely for general information and therefore shall not be binding on the company. We may be bound only through a contract explicitly stipulating such data as binding. Measurement data are laboratory values and can deviate from practical analyses. The manufacture of our products does not involve the use of substances detrimental to health or to the ozone layer.