



COLD WORK STEELS

Available Product Variants

Long Products	Plates	Open Die Forgings

Product Description

BÖHLER K490 MICROCLEAN is a high-performance cold work tool steel with a balanced property profile, manufactured using powder metallurgy. This powder metallurgical tool steel offers an outstanding combination of high wear resistance, compressive strength, toughness and very good machinability. Thanks to the resulting flexibility, BÖHLER K490 MICROCLEAN is used in virtually all cold work applications, and in many cases this material is the first choice for newly developed tools. The commonly used hardening temperatures of BÖHLER K490 MICROCLEAN also enable shared heat treatment with popular cold work tool steels (1.2379, D2), making it very economical in terms of heat treatment.

Process Melting

Powder metallurgy

Properties

> Toughness & Ductility: high

> Wear Resistance : high

> Compressive strength: high

> Dimensional stability: very high

Applications

> Machine knife (for producers)

> Coining

> Screws and Barrels

> Rolls

> Glasfibre reinforced plastics

> Rolling

> Fine Blanking, Stamping, Blanking

> Wear parts

> Components for Recycling Industry

> Cold Forming

> Powder Pressing

> General Components for Mechanical Engineering

> Pill punching dies

Chemical composition (wt. %)

C	C-	Ma	V	l w	NIL
C	CI	Мо	Y	**	IND
1.40	6.40	1.50	3.70	3.50	+







Material characteristics

Compressive strength		Dimensional stability during heat treatment	Toughness	Wear resistance abrasive	Wear resistance adhesive	
BÖHLER K490	***	****	***	***	****	
BÖHLER K100	**	**	*	***	**	
BÖHLER K105	**	**	*	**	**	
BÖHLER K107	**	**	*	***	**	
BÖHLER K110	**	***	* ***		**	
BÖHLER K190	***	****	***	***	****	
BÖHLER K294	****	****	***	****	****	
BÖHLER K340	***	***	**	**	**	
BÖHLER K340	***	***	***	***	***	
BÖHLER K346	***	***	***	***	**	
BÖHLER K353	**	***	**	**	**	
BÖHLER K360	***	***	***	***	***	
BÖHLER K390	****	****	***	****	****	
BÖHLER K497	****	****	***	****	****	
BÖHLER K888	***	****	****	**	**	
BÖHLER K890	***	****	****	***	***	

Delivery condition

۸n	200	ᄾ
All	nea	ıeu

Hardness (HB)	max. 280

Heat treatment

Stress relieving

Hardening and Tempering


Temperature '	°C 1,886 to	Oil, N ₂ Following temperature equalisation: 20 - 30 minutes for a hardening temperature of 1030 - 1080 °C (1885 - 1980 °F). After hardening, tempering to the desired working hardness, see tempering chart.
---------------	---------------	--








Tempering chart



Continuous cooling CCT curves










Quantitative phase diagram



Physical Properties

Temperature (°C °F)	20 68
Density (kg/dm³ lb/in³)	7.79 0.28
Thermal conductivity (W/(m.K) BTU/ft h °F)	19.6 11.32
Specific heat (kJ/kg K BTU/lb °F)	0.45 0.1075
Spec. electrical resistance (Ohm.mm²/m 10 ⁻⁴ Ohm.inch²/ft)	0.55 2.6
Modulus of elasticity (10 ³ N/mm ² 10 ³ ksi)	223 32.34

Thermal Expansions between 20°C | 68°F and ...

Temperature (°C °F)	100 212	200 392	300 572	400 752	500 932	600 1,112	700 1,292
Thermal expansion (10 ⁻⁶ m/(m.K) 10 ⁻⁶ inch/inch.°F)	10.6 5.9	11.1 6.2	11.6 6.4	11.9 6.6	12.3 6.8	12.6 7	12.8 7.1

The data contained in this brochure is merely for general information and therefore shall not be binding on the company. We may be bound only through a contract explicitly stipulating such data as binding. Measurement data are laboratory values and can deviate from practical analyses. The manufacture of our products does not involve the use of substances detrimental to health or to the ozone layer.

voestalpine BÖHLER Edelstahl GmbH & Co KG

Mariazeller Straße 25 8605 Kapfenberg, AT T. +43/50304/20-0 E. info@bohler-edelstahl.at https://www.voestalpine.com/bohler-edelstahl/de/

