

HEAT TREATABLE CORROSION RESISTANT STEELS

Available Product Variants

Long Products

Process Melting

Airmelted + Remelted

Technical data

Material designation
~1.2316 SEL

Chemical composition (wt. %)

C	Si	Mn	Cr	Mo	Ni	N
0.27	0.3	0.65	14.5	1	0.85	+

The data contained in this brochure is merely for general information and therefore shall not be binding on the company. We may be bound only through a contract explicitly stipulating such data as binding. Measurement data are laboratory values and can deviate from practical analyses. The manufacture of our products does not involve the use of substances detrimental to health or to the ozone layer.