

FERRITIC AND MARTENSITIC STEELS, INCL. PRECIPITAION HARDENING STEELS

| | | | | _ | | |
|----|-----|-------|-------|-----|-----|-----|
| ۸n | nli | cati | on 9 | 200 | men | te. |
| Λþ | ווע | lcuti | OII v | JEG | | ıtə |

Engineering

Available Product Variants

Long Products

Product Description

BÖHLER N664 is a corrosion-resistant steel with 17%Cr and Mo-addition in the form of bars, wire, forgings, and forging stock. These products have been used typically for parts in general engineering and cutting and non cutting medical applications, e.g. chisels, knives, osteotomes, scalpels drills, retractors, spreaders, tongs requiring hardness up to 56/57 HRC and resistance to wear, corrosion, and oxidation depending on instrument design and application but usage is not limited to such applications.

Process Melting

Airmelted

Applications

- > Mechanical Engineering
- > Medical
- > Medical Instruments & Implants

- > Food processing Industry
- > Medical Industry

Technical data

| Material designation | | Standards | | |
|----------------------|--------------|------------|------|--|
| 440A | Market grade | A276/A276M | | |
| S44002 | UNS | F899 | ASTM | |
| | | | | |

Chemical composition (wt. %)

| С | Si | Mn | P | S | Cr | Мо |
|--------------|-----------|-----------|------------|------------|--------------|-----------|
| 0.60 to 0.75 | max. 1.00 | max. 1.00 | max. 0.040 | max. 0.030 | 16.0 to 18.0 | max. 0.75 |

Refers to ASTM A276.





FERRITIC AND MARTENSITIC STEELS, INCL. PRECIPITAION HARDENING STEELS



Delivery condition

| Annealed | | | | | |
|---------------|--------------------------|--|--|--|--|
| Hardness (HB) | max. 269 Hot finished | | | | |
| | | | | | |
| Annealed | | | | | |
| Hardness (HB) | max. 285 Cold finished | | | | |

Round Bars and Wire Rod (if any)

| Diameter | | | | | | | |
|----------|---------|-------|---|-------|--|--|--|
| | | inch | | | | | |
| ROLLED | | | | | | | |
| 12.50 | - 65.00 | 0.492 | - | 2.559 | | | |

Further information on MOQ, length and tolerance on request.

For additional specifications and other sizes please contact BÖHLER Edelstahl - Special Materials Engineering

The data contained in this brochure is merely for general information and therefore shall not be binding on the company. We maybe bound only through a contract explicitly stipulating such data as binding. Measurement data are laboratory values and can deviate from practical analyses. The manufacture of our products does not involve the use of substances detrimental to health or to the ozone layer.

voestalpine BÖHLER Edelstahl GmbH & Co KG

Mariazeller Straße 25 8605 Kapfenberg, AT T. +43/50304/20-0 E. info@bohler-edelstahl.at https://www.voestalpine.com/bohler-edelstahl/de/

